


			Slip Resistance			
	Standard	Result	Product	Size (mm)	DIN 51130	DIN 51097
		See separate table	LLP92	1050,0 X 250,0	R10	B
		4,5 mm	LLP93	1050,0 X 250,0	R10	B
		0,55 mm	LLP94	1050,0 X 250,0	R10	B
		Surface treatment	LLP95	1050,0 X 250,0	R10	B
		Guarantee	LLP96	1050,0 X 250,0	R10	B
	Light industrial	10 year	LLP97	1050,0 X 250,0	R10	B
	Commercial	12 year	LLP99	1050,0 X 250,0	R10	B
	Domestic	15 year	LLP101	1050,0 X 250,0	R10	B
		No	LLP102	1050,0 X 250,0	R10	B
	EN 649	Heterogeneous PVC	LLP103	1050,0 X 250,0	R10	B
	EN 685- Light industrial	42: Light industrial general	LLP104	1050,0 X 250,0	R10	B
	EN 685- Commercial	33: Commercial heavy	LLP105	1050,0 X 250,0	R10	B
	EN 685- Domestic	23: Domestic heavy	LLP106	1050,0 X 250,0	R10	B
	EN 13501-1	B _{fl} -s1	LLP108	1050,0 X 250,0	R10	B
	EN ISO 9239-1	Pass	LLP109	1050,0 X 250,0	R10	B
	EN ISO 11925-2	Pass	LLP110	1050,0 X 250,0	R10	B
	EN 423	Class 0	LLP111	1050,0 X 250,0	R10	B
	EN ISO 105-B02	≥7	LLP112	1050,0 X 250,0	R10	B
	EN 660-2	Group T	LLP113	1050,0 X 250,0	R10	B
	EN 434	≤ 0.10%	LLT200	610,0 X 500,0	R10	A
	EN ISO 717-2 / EN ISO 140-8	ΔL _w = 13 db	LLT201	610,0 X 500,0	R10	A
	EN 1815	Pass	LLT202	610,0 X 500,0	R10	A
	EN 433	≤ 0.1mm	LLT203	610,0 X 500,0	R10	A
	EN 425	Pass	LLT204	609,6 X 500,0	R10	A
	EN430	7082 g/m ²	LLT205	609,6 X 500,0	R10	A
	ISO 8302	0,0245 m ² K/W	LLT206	609,6 X 500,0	R10	A
		Suitable for underfloor heating. Max 27°C	LLT207	609,6 X 500,0	R10	A
	DIN 51130	See separate table				
	DIN 51097	See separate table				
	EN 13893	DS				
	NF EN ISO 1600	A+ (<250µg/m ²)				
	Most applications will not require the use of adhesives. However, we recommend the use of a tackifier for heavy traffic areas.					
		Suitable				



Manufactured to:

